

Cubic Ink® High Performance 4-300 VP

Material with a good balance between temperature form-stability and toughness for final part production

Liquid Properties	Value ¹	Unit
Viscosity @ 25 °C (DIN EN ISO 3219)	50	mPa·s
Density (DIN EN ISO 15212-1)	1.08	g/mL
Critical Energy (E _c) @405 / 385 nm	7.9 / 8.2	mJ/cm ²
Depth of Penetration (D _p) @405 / 385 nm	0.78 / 0.24	mm
Tensile Properties² (DIN EN ISO 527-5A)		
Ultimate Tensile Strength	72	MPa
Tensile Modulus	2700	MPa
Elongation at Break	4.6	%
Flexural Properties³ (DIN EN ISO 178)		
Flexural Strength	107	MPa
Flexural Modulus	2500	MPa
Deflection at Fracture	>6.5	%
Impact Properties		
Izod unnotched (DIN EN ISO 180)	240	J/m
Charpy unnotched (DIN EN ISO 179-1)	25	kJ/m ²
Hardness (DIN EN ISO 7619)		
Shore Hardness (green)	75 - 78	D
Shore Hardness	80	D
Thermal Properties		
T _g (TMA) ⁴	96	°C

HDT A (DIN EN ISO 75)	78	°C
HDT B (DIN EN ISO 75)	104	°C
CTE (-50 °C, 50 °C) (DIN EN ISO 11359-2)	71	$\times 10^{-6} \text{ K}^{-1}$
CTE (120 °C, 200 °C) (DIN EN ISO 11359-2)	126	$\times 10^{-6} \text{ K}^{-1}$
Specific Heat Capacity, 20 °C (DIN EN ISO 11357-4)	1.71	J/(g·K)

Electrical Properties

Dielectric strength (IEC60243-1)	22	kV/mm
Dielectric strength after 24 h/RT H ₂ O (IEC60243-1)	22	kV/mm
Relative Permittivity (Dielectric Constant, 24 °C, 1 MHz, IEC60250)	6.5	-
Dissipation Factor (24 °C, 1 MHz, IEC60250)	0.027	-
Volume Resistivity (IEC60093)	5.6×10^{14}	$\Omega \cdot \text{cm}$
Volume Resistivity after 7 d/RT H ₂ O (IEC60093)	2.1×10^{14}	$\Omega \cdot \text{cm}$
Comparative Tracking Index (IEC60112)	>600	V

Flame (UL94)

Flammability, horizontal (at 3.2 mm)	HB	-
--------------------------------------	----	---

Chemical Resistance

Water Uptake, 24 h, 23 °C	0.5	%
Performance after Water Uptake, 168 h, 23 °C ⁵	6	%

Thermal Ageing⁵

120 °C for 3000 hours	5	%
-----------------------	---	---

Print Appearance/ Color

Natural color is translucent light yellow. Also available in cyan, magenta, yellow, black, and grey. More colors on request.


Availability and Storage

Batch sizes starting from 1 kg.


Store between 21 and 28 °C and protect from light. Stir prior to use.

¹Properties with post-processing – washed with water, UV and thermal post-cure. All material properties can vary with printer, print settings, object orientation, part geometry, post-processing and age of sample. ²5 mm/min; ³10 mm/min; ⁴-50 - 200 °C, 5 K/min; ⁵Relative loss of tensile strength compared to reference, DIN EN ISO 527-5A, 5 mm/min.


Versatility and Customization of High Performance 4-Series



Viscosity Profile (600 s⁻¹) of High Performance 4-300 VP



Ageing of High Performance 4-300 VP (points - rel. tensile strength & bars - HDT B)



Chemical Resistance

Mass Gain [%]¹

Water	0.5
Acetic Acid (5%)	0.5
Hydrochloric Acid (1%)	0.5
Nitric Acid (5%)	0.5
Sodium Hypochlorite (10%)	0.4
Hydrogen Peroxide (3%)	0.5
Sodium Hydroxide (1%)	0.4
Isopropyl Alcohol	0.1
Methanol	4.5
Butyl Glycol Acetate	0.1
Super Gasoline	0.2
Acetone	6.0
Methyl Ethyl Ketone	1.4

¹Percental weight gained after 24 h submersion of printed and post-cured (washed with water, UV and thermal post-cure) 1 x 1 x 1 cm cubes.

Cubic Ink®
ACTEGA Terra GmbH
Mielestraße 13
31275 Lehrte
GERMANY

Tel +49 (0)5132 5009-600

cubic.ink@altana.com

www.altana.com

Learn more about Cubic Ink® materials www.altana.com/cubic-ink www.altana.de/cubic-ink

Disclaimer

The information contained herein is based on our current knowledge and experience. No warranties, guarantees and/or assurances of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. Any information about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. Contractual terms and conditions, in particular agreed product specifications, always take precedence. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. We reserve the right to make any changes and to update the information herein without notice.

Follow us – ALTANA New Technologies GmbH – Cubic Ink®



