

Cubic Ink® Rigid 300 VP

Functional prototyping material for industrial applications

Liquid Properties	Value¹	Unit
Viscosity @ 25 °C (DIN EN ISO 3219)	185	mPa·s
Density (DIN EN ISO 15212-1)	1.05	g/mL
Tensile Properties² (DIN EN ISO 527-5A)		
Ultimate Tensile Strength	57	MPa
Yield Strength	57	MPa
Tensile Modulus	2600	MPa
Elongation at Break	4.3	%
Flexural Properties³ (DIN EN ISO 178)		
Flexural Strength	82	MPa
Flexural Modulus	2300	MPa
Deflection at Fracture	>3.5	%
Impact Properties		
Izod notched (DIN EN ISO 180)	15	J/m
Charpy notched (DIN EN ISO 179-1)	2.0	kJ/m ²
Hardness (DIN EN ISO 7619)		
Shore Hardness	82	D
Thermal Properties		
HDT B (DIN EN ISO 75)	59	°C

Thermal Ageing⁴

80 °C for 3000 hours	2	%
----------------------	---	---

Print Appearance/ Color

Natural color is translucent light yellow. Also available in cyan, magenta, yellow, black, white and grey. More colors on request.

Availability and Storage


Batch sizes starting from 1 kg.

Store at room temperature and protect from light.

¹Properties with post-processing – 60 min low-intensity UV-post-cure at 405 nm (LED). All material properties can vary with printer, print settings, object orientation, part geometry, post-processing and age of sample; ²5 mm/min; ³5 mm/min; ⁴Relative loss of tensile strength compared to reference, DIN EN ISO 527-5A, 5 mm/min.

UV Ageing of Cubic Ink® Rigid-series

(points - rel. tensile strength & bars - HDT B)



Cubic Ink[®]
ACTEGA Terra GmbH
Mielestraße 13
31275 Lehrte
GERMANY

Tel +49 (0)5132 5009-600

cubic.ink@altana.com

www.altana.com

Learn more about Cubic Ink[®] materials www.altana.com/cubic-ink www.altana.de/cubic-ink

Disclaimer

The information contained herein is based on our current knowledge and experience. No warranties, guarantees and/or assurances of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. Any information about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. Contractual terms and conditions, in particular agreed product specifications, always take precedence. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. We reserve the right to make any changes and to update the information herein without notice.

Follow us – ALTANA New Technologies GmbH – Cubic Ink[®]

