

Cubic Ink® High Performance 4-1203

Material with a good balance between temperature form-stability and toughness for final part production

Liquid Properties	Value ¹	Unit
Viscosity @ 50 °C (DIN EN ISO 3219)	15	mPa·s
Density (DIN EN ISO 15212-1)	1.08	g/mL
Surface Tension (Dynamic Bubble Pressure)	32	mN/m
Tensile Properties² (DIN EN ISO 527-5A)		
Ultimate Tensile Strength	66	MPa
Yield Strength	66	MPa
Tensile Modulus	3000	MPa
Elongation at Break	6.0	%
Flexural Properties³ (DIN EN ISO 178)		
Flexural Strength	118	MPa
Flexural Modulus	2700	MPa
Deflection at Fracture	>3.5	%
Impact Properties (DIN EN ISO 180)		
Izod unnotched	224	J/m
Hardness (DIN EN ISO 7619)		
Shore Hardness	84	D
Thermal Properties (DIN EN ISO 75)		
HDT A	78	°C
HDT B	100	°C

Electrical Properties⁴

Dielectric strength (IEC60243-1)	22	kV/mm
Dielectric strength after 24 h/RT H ₂ O (IEC60243-1)	22	kV/mm
Relative Permittivity (Dielectric Constant, 24 °C, 1 MHz, IEC60250)	6.5	-
Dissipation Factor (24 °C, 1 MHz, IEC60250)	0.027	-
Volume Resistivity (IEC60093)	5.6 x 10 ¹⁴	Ω·cm
Volume Resistivity after 7 d/RT H ₂ O (IEC60093)	2.1 x 10 ¹⁴	Ω·cm
Comparative Tracking Index (IEC60112)	>600	V

Flame (UL94)

Flammability, horizontal (at 3.2 mm)	HB	-
--------------------------------------	----	---

Print Appearance/ Color


Natural color is translucent light yellow. Also available in cyan, magenta, yellow, black, and grey. More colors on request.

Availability and Storage

Batch sizes starting from 1 kg.

Store between 21 and 28 °C and protect from light. Stir prior to use.

¹Properties with post-processing – washed with water, UV and thermal post-cure. All material properties can vary with printer, print settings, object orientation, part geometry, post-processing and age of sample. ²5 mm/min; ³10 mm/min; ⁴Properties correspond to related product High Performance 4-300 VP.



Cubic Ink®
ACTEGA Terra GmbH
Mielestraße 13
31275 Lehrte
GERMANY

Tel +49 (0)5132 5009-600

cubic.ink@altana.com
www.altana.com

Learn more about Cubic Ink® materials www.altana.com/cubic-ink www.altana.de/cubic-ink

Disclaimer

No warranties, guarantees and/or assurances of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. Contractual terms and conditions, in particular agreed product specifications, always take precedence. Any information about suitability and use of the products is non-binding and does not constitute a commitment regarding the products' specifications or use. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. The information contained herein is based on our current knowledge and experience. We reserve the right to make any changes and to update the information herein without notice.

Follow us – ALTANA New Technologies GmbH – Cubic Ink®

