

Cubic Ink® Rigid 700

Rigid material for fast, accurate prints with sharp edges

Liquid Properties	Value ¹	Unit
Viscosity @ 50 °C (DIN EN ISO 3219)	38	mPa·s
Surface Tension (Dynamic Bubble Pressure)	36	mN/m
Tensile Properties² (DIN EN ISO 527-5A)		
Ultimate Tensile Strength	55	MPa
Tensile Modulus	2700	MPa
Elongation at Break	4.4	%
Flexural Properties³ (DIN EN ISO 178)		
Flexural Strength	93	MPa
Flexural Modulus	2500	MPa
Impact Properties (DIN EN ISO 180)		
Izod unnotched	360	J/m
Hardness (DIN EN ISO 7619)		
Shore Hardness	85	D
Thermal Properties (DIN EN ISO 75)		
HDT B	55	°C
Chemical Resistance		
Water Uptake, 24 h, 23 °C	< 0.1	%
Thermal Ageing⁴		
120 °C for 3000 hours	< 1	%

Print Appearance/ Color


Natural color is translucent light yellow. Also available in cyan, magenta, yellow, black, white and grey. More colors on request.


Availability and Storage

Batch sizes starting from 1 kg.

Store at room temperature and protect from light.

¹Properties with post-processing – 60 min UV-post-cure. All material properties can vary with printer, print settings, object orientation, part geometry, post-processing and age of sample. ²5 mm/min; ³5 mm/min; ⁴Relative loss of tensile strength compared to reference, DIN EN ISO 527-5A, 5 mm/min.





Chemical Resistance

Mass Gain [%]¹

Water	< 0.1
Acetic Acid (5%)	< 0.1
Hydrochloric Acid (1%)	< 0.1
Nitric Acid (5%)	< 0.1
Sodium Hypochlorite (10%)	< 0.1
Hydrogen Peroxide (3%)	< 0.1
Sodium Hydroxide (1%)	< 0.1
Isopropyl Alcohol	0.5
Methanol	2.6
Butyl Glycol Acetate	0.4
Super Gasoline	2.0
Acetone	7.1
Methyl Ethyl Ketone	7.2

¹Percental weight gained after 24 h submersion of printed 1 x 1 x 1 cm³ cubes.

Cubic Ink®
ACTEGA Terra GmbH
Mielestraße 13
31275 Lehrte
GERMANY

Tel +49 (0)5132 5009-600

cubic.ink@altana.com

www.altana.com

Learn more about Cubic Ink® materials www.altana.com/cubic-ink www.altana.de/cubic-ink

Disclaimer

No warranties, guarantees and/or assurances of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. Contractual terms and conditions, in particular agreed product specifications, always take precedence. Any information about suitability and use of the products is non-binding and does not constitute a commitment regarding the products' specifications or use. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. The information contained herein is based on our current knowledge and experience. We reserve the right to make any changes and to update the information herein without notice.

Follow us – ALTANA New Technologies GmbH – Cubic Ink®

