

Cubic Ink® High Performance 2-900 VP

Rigid material with a good temperature form-stability and chemical resistance for final part production

Liquid Properties	Value ¹	Unit
Viscosity @ 25 °C (DIN EN ISO 3219)	360	mPa·s
Density (DIN EN ISO 15212-1)	1.12	g/mL
Critical Energy (E _c) @405 / 385 nm	5.3 / 7.5	mJ/cm ²
Depth of Penetration (D _p) @405 / 385 nm	0.31 / 0.19	mm
Tensile Properties² (DIN EN ISO 527-5A)		
Ultimate Tensile Strength	94	MPa
Tensile Modulus	3400	MPa
Elongation at Break	3.8	%
Flexural Properties³ (DIN EN ISO 178)		
Flexural Strength	118	MPa
Flexural Modulus	3300	MPa
Deflection at Fracture	3.9	%
Impact Properties (DIN EN ISO 180)		
Izod notched (DIN EN ISO 180)	12	J/m
Charpy notched (DIN EN ISO 179-1)	1.2	kJ/m ²
Izod unnotched (DIN EN ISO 180)	240	J/m
Charpy unnotched (DIN EN ISO 179-1)	21	kJ/m ²
Hardness (DIN EN ISO 7619)		
Shore Hardness (green)	60 - 70	A
Shore Hardness	87	D

Thermal Properties (DIN EN ISO 75)

T _g (TMA) ⁴	124	°C
HDT A	115	°C
HDT B	138	°C
CTE (-50 °C, 125 °C) (DIN EN ISO 11359-2)	70	x 10 ⁻⁶ K ⁻¹
CTE (130 °C, 200 °C) (DIN EN ISO 11359-2)	167	x 10 ⁻⁶ K ⁻¹
Specific Heat Capacity, 20 °C (DIN EN ISO 11357-4)	1.6	J/(g·K)

Electrical Properties

Dielectric strength (IEC60243-1)	25	kV/mm
Dielectric strength after 24 h/RT H ₂ O (IEC60243-1)	24	kV/mm
Relative Permittivity (Dielectric Constant, 22 °C, 10000 Hz, IEC60250)	8.1	-
Dissipation Factor (22 °C, 10000 Hz, IEC60250)	0.017	-
Volume Resistivity (IEC60093)	9.7 x 10 ¹⁴	Ω·cm
Volume Resistivity after 7 d/RT H ₂ O (IEC60093)	3.4 x 10 ¹⁴	Ω·cm
Comparative Tracking Index (IEC60112)	>600	V

Flame (UL94)

Flammability, horizontal (at 3.2 mm)	HB	-
--------------------------------------	----	---

Chemical Resistance

Water Uptake, 24 h, 23 °C	0.1	%
Water Uptake, 168 h, 23 °C ⁵	1.0	%
Performance after Water Uptake, 24 h, 23 °C ⁶	<1	%
Performance after Water Uptake, 168 h, 23 °C ⁶	<1	%

Thermal Ageing⁶

125 °C for 1000 hours	5	%
-----------------------	---	---

Ageing at -40 °C⁷

for 168 hours	11	%
---------------	----	---

Print Appearance/ Color




Natural color is translucent yellow. More colors on request.

Availability and Storage

Batch sizes starting from 1 kg.

Store at 8 °C and protect from light.

¹Properties with post-processing – washed with IPA, UV-post-cure followed by a thermal treatment up to 160 °C. All material properties can vary with printer, print settings, object orientation, part geometry, post-processing and age of sample. ²5 mm/min; ³5 mm/min; ⁴-50 - 200 °C, 5 K/min (TMA); ⁵Specimen DIN EN ISO 527-5A weight difference; ⁶Relative loss of E-modulus, DIN EN ISO 527-5A, 5 mm/min; ⁷Relative loss of HDT B.



Chemical Resistance	Mass Gain [%]¹	Performance Loss [%]²
Water	0.1	4
Acetic Acid (5%)	0.2	3
Hydrochloric Acid (1%)	0.1	<1
Nitric Acid (5%)	0.1	<1
Sulfuric Acid (30%)	0.2	<1
Sodium Hypochlorite (10%)	0.1	<1
Hydrogen Peroxide (3%)	0.2	3
Hydrogen Peroxide (30%)	0.2	3
Sodium Hydroxide (1%)	0.2	6
Sodium Hydroxide (10%)	0.2	6
Isopropyl Alcohol	<0.1	3
Ethanol	0.1	<1
Methanol	1.3	12
Butyl Glycol Acetate	<0.1	<1
Super Gasoline	<0.1	<1
Acetone	0.5	<1
Methyl Ethyl Ketone	<0.1	<1

¹Percental weight gained after 24 h submersion of printed and post-cured (IPA-washed, UV-post-cure followed by a thermal treatment up to 160 °C) 1 x 1 x 1 cm cubes; ²Relative loss of E-modulus, DIN EN ISO 527-5A, 5 mm/min after 24 h submersion.

Cubic Ink®
ACTEGA Terra GmbH
Mielestraße 13
31275 Lehrte
GERMANY

Tel +49 (0)5132 5009-600

cubic.ink@altana.com

www.altana.com

Learn more about Cubic Ink® materials www.altana.com/cubic-ink www.altana.de/cubic-ink

Disclaimer

No warranties, guarantees and/or assurances of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. Contractual terms and conditions, in particular agreed product specifications, always take precedence. Any information about suitability and use of the products is non-binding and does not constitute a commitment regarding the products' specifications or use. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. The information contained herein is based on our current knowledge and experience. We reserve the right to make any changes and to update the information herein without notice.

Follow us – ALTANA New Technologies GmbH – Cubic Ink®

