

## Cubic Ink® High Performance 4-1000 VP

Flame retardant material with a good balance between temperature form-stability and toughness for final part production

Liquid Properties	Value <sup>1</sup>	Unit
Viscosity @ 25 °C (DIN EN ISO 3219)	460	mPa·s
Density (DIN EN ISO 15212-1)	1.05	g/mL
Critical Energy (E <sub>c</sub> ) @405 / 385 nm	8.7 / 10.0	mJ/cm <sup>2</sup>
Depth of Penetration (D <sub>p</sub> ) @405 / 385 nm	0.60 / 0.30	mm
<b>Tensile Properties<sup>2</sup> (DIN EN ISO 527-5A)</b>		
Ultimate Tensile Strength	97	MPa
Tensile Modulus	4500	MPa
Elongation at Break	2.7	%
<b>Flexural Properties<sup>3</sup> (DIN EN ISO 178)</b>		
Flexural Strength	130	MPa
Flexural Modulus	4100	MPa
Deflection at Fracture	>3.5	%
<b>Impact Properties</b>		
Izod notched (DIN EN ISO 180)	14	J/m
Charpy notched (DIN EN ISO 179-1)	1	kJ/m <sup>2</sup>
Izod unnotched (DIN EN ISO 180)	220	J/m
Charpy unnotched (DIN EN ISO 179-1)	19	kJ/m <sup>2</sup>
<b>Hardness (DIN EN ISO 7619)</b>		
Shore Hardness	88	D

## Thermal Properties

T <sub>g</sub> (TMA) <sup>4</sup>	80	°C
HDT A (DIN EN ISO 75)	98	°C
HDT B (DIN EN ISO 75)	123	°C
CTE (-50 °C, 30 °C) (DIN EN ISO 11359-2)	53	x 10 <sup>-6</sup> K <sup>-1</sup>
CTE (70 °C, 200 °C) (DIN EN ISO 11359-2)	141	x 10 <sup>-6</sup> K <sup>-1</sup>

## Electrical Properties

Dielectric strength (IEC60243-1)	23	kV/mm
Relative Permittivity (Dielectric Constant, 20 °C, 1 MHz, IEC60250)	7.3	-
Dissipation Factor (20 °C, 1 MHz, IEC60250)	0.058	-
Volume Resistivity (IEC60093)	3.3 x 10 <sup>11</sup>	Ω·cm
Comparative Tracking Index (IEC60112)	200	V

## Flame (UL94)

Flammability, vertical (at 3.2 mm)	V-0	-
Flammability, horizontal (at 0.4 mm)	HB (FH-1)	-

## Chemical Resistance

Water Uptake, 24 h, 23 °C	2.1	%
Performance after Water Uptake, 24 h, 23 °C <sup>5</sup>	46	%

## Print Appearance/ Color

Natural color is translucent light yellow. Available in black and grey. More colors on request.


## Availability and Storage

Batch sizes starting from 1 kg.


Store between 21 and 28 °C and protect from light. Stir prior to use.


<sup>1</sup>Properties with post-processing – washed with water, UV and thermal post-cure. All material properties can vary with printer, print settings, object orientation, part geometry, post-processing and age of sample. <sup>2</sup>5 mm/min; <sup>3</sup>10 mm/min; <sup>4</sup>20 - 280 °C, 5 K/min; <sup>5</sup>Relative loss of HDT B compared to reference.

## Versatility and Customization of High Performance 4-Series



## Viscosity Profile (600 s<sup>-1</sup>) of High Performance 4-1000 VP





### Chemical Resistance

### Mass Gain [%]<sup>1</sup>

Water	2.1
Acetic Acid (5%)	2.0
Hydrochloric Acid (1%)	1.4
Nitric Acid (5%)	2.1
Sodium Hypochlorite (10%)	0.9
Hydrogen Peroxide (3%)	2.3
Sodium Hydroxide (1%)	1.0
Isopropyl Alcohol	0.2
Methanol	0.9
Butyl Glycol Acetate	0.2
Super Gasoline	0.2
Acetone	0.2
Methyl Ethyl Ketone	0.2

<sup>1</sup>Percental weight gained after 24 h submersion of printed and post-cured (washed with water, UV and thermal post-cure) 1 x 1 x 1 cm cubes.

**Cubic Ink<sup>®</sup>**  
**ACTEGA Terra GmbH**  
Mielestraße 13  
31275 Lehrte  
GERMANY

Tel +49 (0)5132 5009-600

[cubic.ink@altana.com](mailto:cubic.ink@altana.com)

[www.altana.com](http://www.altana.com)

**Learn more about Cubic Ink<sup>®</sup> materials** [www.altana.com/cubic-ink](http://www.altana.com/cubic-ink) [www.altana.de/cubic-ink](http://www.altana.de/cubic-ink)

#### Disclaimer

No warranties, guarantees and/or assurances of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. Contractual terms and conditions, in particular agreed product specifications, always take precedence. Any information about suitability and use of the products is non-binding and does not constitute a commitment regarding the products' specifications or use. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. The information contained herein is based on our current knowledge and experience. We reserve the right to make any changes and to update the information herein without notice.

**Follow us – ALTANA New Technologies GmbH – Cubic Ink<sup>®</sup>**

