

Cubic Ink® Mold 2000 VP

Water-breakable cast material compatible with various (2K-)filling compounds

Liquid Properties	Value ¹	Unit
Viscosity @25 °C (DIN EN ISO 3219)	70	mPa·s
Density (DIN EN ISO 15212-1)	1.11	g/mL
Critical Energy (E _c) @385 nm	1.1	mJ/cm ²
Depth of Penetration (D _p) @385 nm	0.12	mm
Tensile Properties² (DIN EN ISO 527-5A)		
Ultimate Tensile Strength	38	MPa
Yield Strength	37	MPa
Tensile Modulus	1800	MPa
Elongation at Break	45	%
Hardness (DIN EN ISO 7619)		
Shore Hardness	82	D
Print Appearance/ Color		
Natural color is light yellow. Also available in cyan, magenta, yellow, black, white and grey. More colors on request.		
Availability and Storage		
Batch size starting from 1 kg.		
Store at room temperature and protect from light. Stir prior to use.		
¹ Properties may vary with post-processing – 30 min UV-post-cure. All material properties can vary with printer, print settings, object orientation, part geometry, post-processing and age of sample. ² 5 mm/min.		

Compatible filling materials¹

2K Silicone

2K Epoxide

2K Polyester

Low-melting metals and allows

Composites (e.g. Epoxide / Glass Fiber)

¹The compatibility strongly depends on the geometry of the final part.



Figure 1: Examples of printed mold and final object, shown for a glass fiber-filled 2K epoxide (left) and the 'Fieldsche Metal' as low-melting allow (right).

ACTEGA Terra GmbH

Mielestraße 13
31275 Lehrte
GERMANY

Tel +49 (0)5132 5009-600

cubic.ink@altana.com
www.altana.com

Learn more about Cubic Ink[®] materials www.altana.com/cubic-ink www.altana.de/cubic-ink

Disclaimer

The information contained herein is based on our current knowledge and experience. No warranties, guarantees and/or assurances of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. Any information about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. Contractual terms and conditions, in particular agreed product specifications, always take precedence. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. We reserve the right to make any changes and to update the information herein without notice.

Follow us – ALTANA New Technologies GmbH –

